

DISPERBYK-180

Solvent-free wetting and dispersing additive for solvent-borne, solvent-free and aqueous coating systems, printing inks and adhesives for stabilizing inorganic pigments, in particular titanium dioxide.

Product Data

Composition

Alkylol ammonium salt of a copolymer with acidic groups

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value:	94 mg KOH/g
Acid value:	94 mg KOH/g
Active substance content:	100 %
Density (20 °C):	1.08 g/ml

Storage and Transportation

Mix well before use. Separation or turbidity may occur. Heat to 30-40 °C and stir.

Applications

Coating Industry, Printing Inks and Adhesives

Special Features and Benefits

The additive deflocculates pigments by means of steric stabilization. As a result of the small particle sizes of the deflocculated pigments, high levels of gloss can be achieved and the color strength is improved. Transparency and hiding powder also increase and viscosity is reduced. In this way, the flow characteristics are also improved and higher pigment loading is possible.

Recommended Use

The additive is recommended for all aqueous, solvent-borne and solvent-free systems to stabilize inorganic pigments, specifically titanium dioxide.

Recommended Levels

Amount of additive (as supplied) based upon pigment.

Inorganic pigments:	5-10 %
Titanium dioxide:	1.5-2.5 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive must be incorporated into the millbase before addition of pigments. The resin and solvent components of the millbase are pre-mixed and then the additive is slowly incorporated while stirring continuously. Do not add the pigments until the additive has been fully distributed.

DISPERBYK-180

Data Sheet
Issue 01/2021



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-DYNWET®, BYK-MAX®, BYK-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOÍSITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITÉ®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany